

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

## TEST REPORT

**Client :** Supertuft Pty Ltd  
14 Prince Patrick Street  
Richmond VIC 3121

**Test Number :** 20-000852  
**Issue Date :** 2/03/2020  
**Print Date :** 2/03/2020

**Sample Description** Clients Ref : "Escape Velour/Airstep Supa Blue"  
Cut pile tufted carpet  
Nominal Composition : 100% Wool  
Nominal Mass per Unit Area/Density : 1630g/m2  
Nominal Thickness : 10mm

### AS/ISO 9239.1-2003

#### Reaction to Fire Tests for Floorings. Determination of the Burning Behaviour using a Radiant Heat Source

Date of Sample Arrival 17/02/2020

Date Tested 28/02/2020

CHF Value	1	2	3	Mean
Length	5.0	-	-	- kW/m <sup>2</sup>
Width	4.5	5.2	5.0	4.9 kW/m <sup>2</sup>
Smoke Value	1	2	3	Mean
Length	47	-	-	- % .min
Width	96	81	75	84 % .min

Melting Yes

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23±2°C and relative humidity of 50±5% for a minimum of 48 hours prior to testing.

HF30 not reported as flame out time occurred before 30 minutes.

Results in accordance with section 8.4 have not been included in the report. They are available upon request.

195933

42538

Page 1 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR

# AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing

A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O Box 240, North Melbourne, Victoria 3051

Phone (03) 9371 2400

## TEST REPORT

**Client :** Supertuft Pty Ltd  
14 Prince Patrick Street  
Richmond VIC 3121

**Test Number :** 20-000852  
**Issue Date :** 2/03/2020  
**Print Date :** 2/03/2020

Each specimen was loose laid over Airstep SupaBlue underlay and 6mm thick fibre reinforced cement board and clamped prior to testing.

195933

42538

Page 2 of 2

© Australian Wool Testing Authority Ltd  
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing

- Chemical Testing  
- Mechanical Testing  
- Performance & Approvals Testing

: Accreditation No. 983  
: Accreditation No. 985  
: Accreditation No. 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)  
MANAGING DIRECTOR